

Waterproofing Systems / Capillary Waterproofing Systems**AQUAFIX®****Crystallized Waterproofing Material****DESCRIPTION**

Cement-based, **crystallized** waterproofing material that can be applied in both **positive** and **negative** hydrostatic pressure directions and becomes reactive with water and moisture. It reacts with water, moisture and free lime in the concrete and penetrates deeply into the concrete thanks to its formula consisting of **cement, chemicals** and **specially selected fine aggregates**. It creates insoluble minerals in capillary spaces and pores.

APPLICATION AREAS**Negative Water Pressure:**

- Interior waterproofing of basement walls and foundations,
- Exterior waterproofing of water tanks that are not in the ground,
- Retaining walls,
- Tunnels and subways
- Floors and horizontal joints
- Elevator pits.

Positive Water Pressure:

- Groundwork and curtain walls
- Water tanks (from both interior and exterior positive waterproofing of the water tanks that are underground)
- Swimming pools,
- Irrigation canals,
- Concrete pipes,
- Tunnels and culverts,
- Dams,
- Cisterns.

TECHNICAL PROPERTIES

Appearance	Red or grey colored fine powder
Powder Density	~ 1.20 kg/L
Water/Aquafix Mixing Rate	Curtain Walls: 9 – 10 L water / 25 kg powder Cold Joints: 6.5 – 7.5 water / 25 kg powder
Resting Period	3 - 5 minutes
Pot Life	20 – 40 minutes
Setting Time	30 - 60 minutes
Service Temperature	-20°C / +70°C

ADVANTAGES

- Applied from the direction of both **positive** and **negative** hydrostatic pressure.
- Integrates with the concrete surface and penetrates in depth into the concrete. Minerals formed after its reaction fill the capillary spaces. It insulates the concrete both from the surface and in the volume.
- Since it is reactive, it continues to react with water molecules throughout the life of the reinforced concrete and provides waterproofing during the service life of the structure.
- Sub-foundation sprinkle can be done in any weather condition where concrete can be poured. However, if there is a puddle on lean concrete in rainy weather, concrete pouring and dry sprinkling should be done at the same time.
- Its red and grey colors provide ease of application and control.
- There is no need to prime before its application, water curing is sufficient.
- AQUAFIX slurry application is extremely easy and effective against the insulation problem that will occur in horizontal joints.
- Since it fills the capillary gaps in the concrete and the cracks that may occur up to 0.5 mm in the concrete, it prevents the penetration of water, moisture and sulphate into the concrete.
- Protects the concrete from chemical and physical damages caused by sulfate attacks, prevents the corrosion of reinforcement.
- Penetrates the concrete and does not form an insulating layer, XPS, drainage board and protection wall are not required before backfilling.

- Air and water permeable, allows the structure to breathe. Prevents moisture and odor.
- Can be applied on unset concrete, new concrete and old concrete.
- Is not affected from UV and oxidation.
- Saves time and labor, is economical.
- Resistant to freeze - thaw cycle
- Not poisonous. Ideal for potable water tanks.

CONSUMPTION

Under Foundations	Dry Sprinkle	3 kg/m ²
Curtain Walls	Plaster	Positive water pressure: 2 kg/m ² (2 layers) Negative water pressure: 2.5 kg/m ² (2 layers)
Cold Joints	Slurry	3 kg/m ²

PACKAGING

25 kg craft bags

APPLICATION

PREPARATION OF THE SURFACE**1. UNDER FOUNDATIONS**

There is no need to make any surface preparation for dry sprinkle.

2. CURTAIN WALLS

- The surface must be clear of dust, oil, tar, bitumen, paint, silicone, curing material, detergent and mold oils that prevent penetration.
- Repair the segregations and static cracks in the concrete with **AQUAFIX EXPAN High Strength Non-shrinkage Waterproofing Structural Repair Mortar** that contains active material. Repair the dynamic (moving) cracks with FIXA's appropriate MS, hybrid or polyurethane sealants. Fill the rod holes and bevel horizontal-vertical cold joints with **AQUAFIX EXPAN**. Block water incoming holes with **AQUASTOP**.

3. COLD JOINTS

The surface must be clear of any material that prevents bonding.

PREPARATION OF THE MORTAR

Add mixing water to the AQUAFIX powder placed in a clean mixing bowl. Never do the opposite and always mix only the amount of material you can use within the pot life. Add the water slowly to AQUAFIX and mix with a 400 – 600 rpm mixer for 3 – 5 minutes until it is homogeneous and lump-free. Add 25 kg of AQUAFIX powder in 6.5 – 7.5 L water for use as slurry, in 9 – 10 L water for plaster. Leave the mixture to rest for 3 – 5 minutes and mix again for 30 seconds before use.

APPLICATION

There are 3 different application methods of AQUAFIX:

- Dry Sprinkle:** For the right amount of consumption, create 2 m x 3 m (6 m²) slabs after the molds are fixed on the lean concrete and the raft reinforcements are connected. Place the bags of 25 kg of AQUAFIX into the slabs and spread the content of each bag into the slabs over the iron reinforcement with a consumption of 3 kg/m², just before the raft foundation concrete is poured. It is applied as dry sprinkle as the existing water molecules in the unset concrete are sufficient for AQUAFIX to react.
- Slurry:** Add 25 kg of powder AQUAFIX to 6.5 - 7.5 liters of water and pour the thick viscous slurry on horizontal and vertical cold joints before the mold is closed or apply with a brush. In cases where hydrostatic pressure is high, it is recommended to use **IMPERMO ACRYL-300 Acrylic Based Water Swelling Tape** or **IMPERMO Sodium Bentonite Based Water Swelling Tape** for cold joints.
- Plaster:** Saturate the surface with water and keep it moist on foundation side and curtain concrete surfaces. Add 25 kg of AQUAFIX to 9 – 10 liters of water and apply to the surface with a brush, with a total consumption of 2 kg/m², 1 kg/m² on each layer. (For monitoring the application, it is recommended to use red AQUAFIX in the first layer and grey AQUAFIX in the second layer.) Apply the second layer within approximately 3-4 hours after the first layer is set but not completely dry. Spray water for curing for 3 – 4 days after the application for curing.

It is recommended to waterproof with AQUAFIX plaster application from the negative side due to segregations and cold joints that may occur in curtain concrete when **AQUAFIX LIQUID Crystallized Capillary Waterproofing Concrete Admixture** poured from one-side using mold. Use **AQUAFIX EXPAN High Strength Non-shrinkage Waterproofing Structural Repair Mortar** for repairs and bevelling.

CAUTION

- Application in temperatures between +5°C and +35°C will increase the product performance on curtain walls and cold joints.
- Avoid application in frozen areas, areas where there is a risk of freezing within 24 hours or open to direct sun and wind.
- Do not add powder and water to the expired mortar. Stir frequently to maintain the consistency of the mortar during application.
- Since water pressure accelerates the formation of crystals and the penetration of AQUAFIX into the concrete, fill the structures such as water tanks with water 24 hours after the last layer of AQUAFIX. A complete waterproofing is usually achieved after 5 – 7 days. Fill the soil at the end of this period.
- The formation of minerals in the concrete and the depth of their penetration into the concrete depend on the quality of the concrete, the capillary void ratio in the concrete and the absorbency of the surface. The better the curing with water, the better the material will penetrate into the concrete. Do not use any other curing liquid other than water.
- The crystals formed by AQUAFIX can create an undecorative appearance on curtain walls isolated from negative side. In order to prevent this, plaster when the last layer of AQUAFIX is still wet and paint on the plaster. If the area will be covered with ceramic or tile, apply the ceramic adhesive directly on the freshly applied AQUAFIX. If the coverings will be done on cured AQUAFIX, wipe the crystals on the surface with diluted hydrochloric acid or bleach, then apply the plaster on it. This wiping process only destroys the crystals on the surface, does not damage the crystals that have penetrated into the concrete.
- Use protective glasses and gloves during application.

SHELF LIFE

Unopened packages can be stored in a dry environment for 12 months, stacked maximum 10 packages.

HEALTH AND SAFETY

As with all chemical products, avoid contact with food, skin, eyes and mouth during usage and storage. During the application, use work clothes, protective gloves, goggles and mask in accordance with the occupational and worker health regulations. Consult a doctor if accidentally swallowed. In case of contact with skin, rinse with water. Keep out of reach of children.



Technical Data Sheet (TDS)

Form No: 5.01 TDS Aquafix
Rev: 03 – 08/2022

Date
01 August 2022

Page
4 / 4

* The application instructions and technical values given for the products have been obtained in our tests in accordance with international standards and our experience, at $23 \pm 2^{\circ}\text{C}$ temperature and $50 \pm 5\%$ relative humidity. These values may vary depending on ambient conditions. High temperatures shorten the durations, low temperatures extend them. Before starting the application, whether the product is suitable for the application and purpose should be tested by the user. FIXA Construction Chemicals is not responsible for application errors that may occur if the product is used outside of its intended purpose or if the application conditions and recommendations mentioned above are not followed. This Technical Data Sheet is valid until the next revision is published. FIXA reserves the right to change the values specified in this Technical Data Sheet, provided that a new version is published. It is the user's responsibility to check the currency of the document. For more information, please contact our sales department.