

Tile and Ceramic Adhesives / Cement Based Adhesives**FIXA**[®]**Natural Stone and Brick Adhesive Mortar****DESCRIPTION**

Cement based, single component, polymer added, **flexible, thick bed** adhesive mortar with reduced slip and high performance and stability.

APPLICATION AREAS

- Indoor and outdoor
- Horizontal and vertical surfaces
- Bonding covering materials such as natural stone, granite, marble, brick or bigger sized ceramics
- Bonding floor coverings on imperfect surfaces without combing.

TECHNICAL PROPERTIES

Appearance	Grey colored coarse powder
Powder Density	~ 1.60 kg/L
Water Mixing Ratio	5 - 6 L water / 25 kg powder
Resting Period	5 - 10 minutes
Pot Life	1.5 - 2 hours
Application Temperature	Between +5°C and +35°C
Tensile Adhesion Strength	≥ 1 N/mm ² (28 days) (EN 1348)
Slip	≤ 0.5 mm (EN 1308)
Walk-on Time	24 hours
Service Temperature	-30°C / +80°C

ADVANTAGES

- Flexible and provides strong bonding
- Resistant to water and frost
- Not affected by temperature changes
- Provides high stability and does not sag in vertical applications
- Covering can be made on floors without applying screeds initially.

CONSUMPTION

Varies depending on the surface.

PACKAGING

25 kg kraft bags

APPLICATION

PREPARATION OF THE SURFACE

- The surface must be cured.
- The surface must be clear of materials that prevent bonding, such as dust, oil, tar, paint, silicone, curing materials, detergents and mold oils.
- Repair the surface 24 hours before the application with **FIXA's** appropriate repair mortars depending on the depth and structure of the surface.
- Wet the surface and keep it moist. If the surface is very absorbent, prime it before the application.
- In wet areas, isolate the surface with **FIXA's** appropriate waterproofing materials before the use of the ceramic adhesive.

PREPARATION OF THE MORTAR

- Add 25 kg of **FIXA** Natural Stone and Brick Adhesive Mortar in approximately 5 – 6 L of clean water and mix with a low speed mixer until there are no lumps.
- Let the mortar rest to mature for 5 – 10 minutes and mix again 1 – 2 minutes before use.
- Use the material within 1.5 – 2 hours.

APPLICATION

- Apply the mortar preferably with a trowel both on the back of the coating material and on the surface, preferably with a double-sided adhesion method.
- Apply the coating on the adhesive within 15 - 20 minutes.
- To ensure a good adhesion, apply force with a rubber hammer.
- For applications exceeding 3 m, use mechanical fixing profiles depending on the weight of the natural stone to be bonded.
- Complete the application by using the appropriate **FIXA** joint filler, leaving a joint gap compatible with the ceramic size.

CAUTION

- Avoid application at temperatures below +5°C and above +35°C.
- Do not add water more than necessary.
- Avoid application in areas that are frozen, at risk of freezing within 24 hours, or in areas open to direct sun and wind.
- Do not add water or powder to the expired product.

SHELF LIFE

Expires in 12 months. Store unopened packages in a dry environment, stack up to 10 packages on the pallet.

HEALTH AND SAFETY

As with all chemical products, avoid contact with food products, skin, eyes and mouth during use and storage. During the application, use work clothes, protective gloves and glasses in accordance with the occupational and worker health rules. Consult a doctor if accidentally swallowed. In case of contact with skin, rinse with water. Do not leave the cover open. Store out of the reach of children.

The application instructions and technical values given for the products have been obtained in accordance with our tests and experiences in accordance with international standards at 23±2°C temperature and 50±5% relative humidity conditions. These values may vary depending on ambient conditions. High temperatures shorten the times, low temperatures lengthen them. Before starting the application, the user should test whether the product is suitable for the application and purpose. **FIXA** Yapı Chemicals San. Trade Ltd. Sti. is not responsible. This Technical Data Sheet remains valid until the next revision is published. **FIXA** reserves the right to change the values specified in this Technical Data Sheet, provided that the new version is published. It is the user's responsibility to check that the document is up-to-date. Please contact our sales department for more information.