

Waterproofing Systems / Waterproofing Tapes and Subsidiary Products

IMPERMO

Sodium Bentonite Based Water Swellable Tape

DESCRIPTION

Sodium bentonite and butyl rubber based **water swellable** tape for joints. Makes concrete joints waterproof by swelling upon contact with water.

APPLICATION AREAS

- Indoor and outdoor
- Swimming pools, water tanks and purification facilities
- Joints of foundation and shear wall
- Manholes
- Pipe inlet-outlets
- Construction joints in cable canals
- Tunnel segments
- Joints of fresh and old concrete
- Construction joints.

Technical Properties

Appearance	Dark blue colored tape roll
Resistance to Water Pressure	≥ 7 bar (7 days in water)
Hardness (Shore A)	~ 35
Elongation at Break	> 250% (DIN 73521)
Volume Change	After 7 days in water ≥ 200%** (DIN 73521) After 14 days in water ≥ 300%** (DIN 73521) After 10 dry/wet cycle* ≥ 200%** (DIN 73521) <i>*1 cycle 7 days dry and 7 days in water</i> <i>**The amount of CaCO₃ and salt in the water may change the expansion rates.</i>
Application Temperature	Between -20°C and +50°C

ADVANTAGES

- Easy to apply, minimizes user errors that may appear on other water stop tapes,
- Fills cracks and pores that may appear on cold concrete joints by swelling once it gets in contact with water. Makes concrete joints waterproof.
- Can be conveniently used in vertical and horizontal applications.
- Once IMPERMO Sodium Bentonite Based Water Swellable Tape gets in contact with water; it swells in normal speed and does not damage the fresh concrete
- Does not require welding at the joints.

CONSUMPTION

Running meter

PACKAGING

5 mm x 20 mm, in rolls of 10 m
10 mm x 20 mm, in rolls of 5 m

APPLICATION

PREPARATION OF THE SURFACE

- The surface must be clear of materials that prevent bonding, such as dust, oil, tar, paint, silicone, curing materials, detergents and mold oils.
- The surface may be dry or slightly damp. It is recommended not to apply on wet, snowy surfaces in rainy weather.
- Very rough surfaces may cause water leakage after application. It is recommended to smooth the surface where the water swelling tape will be placed with a trowel or a piece of wood before the concrete hardens.

APPLICATION

- Cut sufficient amount of product with scissors or utility knife.
- Fix IMPERMO Sodium Bentonite Based Water Swellable Tape to the center of the section to be applied by mechanical or adhesive methods. Press to the surface for at least 15 seconds.
- If necessary, the tape can be adhered to the surface with **REPOX 310 Epoxy Repair, Adhesive and Assembly Mortar**.
- Joints should be side by side or end to end, not overlapped.
- Make sure that the tape touches each point on reinforced concrete surfaces that are not properly shaped, with aggregates on the surface.
- Peel off the silicone sealant.
- IMPERMO Sodium Bentonite Based Water Swellable Tape can be poured over concrete in a way that will not damage it.
- In applications made in pipe inlet - outlet details, it is not recommended to cover IMPERMO ACRYL-300 Acrylic Based Water Swelling Tape with a cement based product, because the tape will crack the coating as it will swell with water, prefer epoxy based repair mortar.

CAUTION

- Do not remove the product from its packaging until it is to be used.
- After application, avoid in contact with water until it is covered with concrete.
- Do not apply under heavy rain.
- Avoid exposition to direct sunlight and heat.
- The hardness and salt content of the water affects the swelling values of the tape.
- Store in a cool and dry environment and in its original moisture-proof packaging.
- Not suitable for use on joints exposed to movement.

SHELF LIFE

Expires in 12 months. Store unopened packages in a dry environment.

HEALTH AND SAFETY

As with all chemical products, avoid contact with food products, skin, eyes and mouth during use and storage. During the application, use work clothes, protective gloves and glasses in accordance with the occupational and worker health rules. Consult a doctor if accidentally swallowed. In case of contact with skin, rinse with water. Store out of the reach of children.

The application instructions and technical values given for the products have been obtained in accordance with our tests and experiences in accordance with international standards at 23±2°C temperature and 50±5% relative humidity conditions. These values may vary depending on ambient conditions. High temperatures shorten the times, low temperatures lengthen them. Before starting the application, the user should test whether the product is suitable for the application and purpose. FIXA Yapı Chemicals San. Trade Ltd. Sti. is not responsible. This Technical Data Sheet remains valid until the next revision is published. FIXA reserves the right to change the values specified in this Technical Data Sheet, provided that the new version is published. It is the user's responsibility to check that the document is up-to-date. Please contact our sales department for more information.