

**Repair, Reinforcement and Restoration /
Cement Based Repair and Grout Mortars**

REPAIRGROUT GP-S F65

Shrinkage Compensated Flowable Sulphate Resistant Grout and Anchoring Mortar

DESCRIPTION

Cement based, single component, **shrinkage compensated, high strength** grout and anchoring mortar in **fluid consistency**. Complies with class **R4**, does not segregate or bleed. **Resistant to sulphate**.

APPLICATION AREAS

- Indoor and outdoor,
- As a fluid mortar, in hard to reach areas (under soil and water etc.) of reinforced concrete buildings which are exposed to sulphate and corrosive salts
- Repairing bridges, canals and ports thanks to its resistance to the sulphate
- Maintenance and repair of marine buildings
- Anchoring and bedding of machinery feet,
- Repairs that require early high strength,
- Filling and strengthening the gaps and voids between column and beam conjunctions,
- Repairs of concrete that is exposed to segregation by using mold.

TECHNICAL PROPERTIES

Appearance	Grey colored powder
Powder Density	~ 1.40 kg/L
Water Mixing Ratio	3.36 L water / 20 kg powder
Resting Period	2 - 3 minutes
Application Temperature	Between +5°C and +35°C
Compressive Strength	1 day : ≥ 30 N/mm ² (EN 12190) 7 days : ≥ 50 N/mm ² (EN 12190) 28 days : ≥ 65 N/mm ² (EN 12190)
Application Thickness / Layer	Min. 10 mm, Max. 50 mm
Walk-on Time	24 hours

ADVANTAGES

- Resistant to sulphate and corrosive salt attacks, protects reinforced concrete buildings against segregation.
- Due to its fluidity, it can grout gaps which are hard to access and can be applied easily with a pump.
- Prevents shrinkage after setting.
- High strength and fluid concrete can be obtained by mixing with number I clean aggregate by 25%.
- Has early compressive strength.
- Resistant to oil and water permeability due to its high density.
- Does not contain metallic aggregate and chloride.
- Just mixed with water and easy to apply.

CONSUMPTION

Aprr. 18 - 20 kg/m² (for 10 mm thickness)
2 kg powder is used for 1 L mortar.

APPLICATION

PREPARATION OF THE SURFACE

- The application surface must be cured.
- The surface must be free of weakly adhered parts and clear of materials which prevent bonding, such as dust, oil, paint, curing agents, detergents and mold release oils.
- Locate and balance the feet of the machine; do not change its position.
- Wet the surface and keep it moist, but remove completely the excess water ponding on the surface.
- Close the active water leaks on the surface with a suitable plug and drain the water leak.
- Molds must be solid to prevent leakage, the area must be protected from any vibration until the mortar sets.
- Place the mortar whose expansion force is desired to be used at maximum level, in a rectangular cavity with vertical sides. The minimum acceptable depth is 6 mm. If it is desired to be used as a coating, the recommended maximum thickness is 50 mm.

PREPARATION OF THE MORTAR

First, add half of the powder in a 20 kg bag to 3.36 liters of water and mix with a mixer with low speed (400 - 600 rpm) until there are no lumps. Then add the rest of the powder. Mix for at least 5 minutes. 10 liters mortar is obtained.

APPLICATION

- Apply the mortar with a trowel, between 10 – 50 mm on each layer. Pour the mortar uninterruptedly from only one side of the mold to prevent air entrapment. For thicker application, apply the second layer to the surface in the same way when the first layer is dry.
- Do not expose to vibration, locate with a steel wire.
- Place a metal string or chain inside the mold to help spread the mortar over large areas and prevent air bubbles. If a chain is to be used, move the chain in short and rapid oscillations before the mortar begins to set.
- Remove the molds in approximately 24 hours.
- It must be cured immediately after the application. Continuing curing at normal temperature for a week is good for increasing the durability, strength and other properties of the material.
- Deficiencies in curing can reduce the initial expansion required to compensate for subsequent shrinkage.
- Do not operate the machines until the grout mortar sets (approximately 24 hours)

CAUTION

- Avoid application at temperatures below +5°C and above +35°C.
- Be extremely sensitive in water ratios. Mix it with a low-speed mixer and do not mix manually.
- Do not use as a finishing floor covering material on large surfaces.
- If the ambient temperature is below +8°C, cover the floor and keep the mortar at minimum +8°C.
- Avoid application in areas that are frozen, at risk of freezing within 24 hours, or in areas open to direct sun and wind.
- Do not add water and powder to the expired mortar.

PACKAGING

20 kg kraft bags

SHELF LIFE

Expires in 12 months. Store unopened packages in non-humid environments. Stack up to 10 packages on the pallet.



Technical Data Sheet (TDS)

Form No: 5.01 TDS Repairgrout GP-S F65
Rev: 03 – 08/2022

Date
01 August 2022

Page
3 / 3

HEALTH AND SAFETY

As with all chemical products, contact with food, skin, eyes and mouth should be avoided during usage and storing. During the application, work wears, protective gloves and goggles should be used according to the work place health regulations. If swallowed by accident, consult a doctor. Rinse with water in case of contact with skin. Keep out of reach of children.

The application instructions and technical values given for the products have been obtained in accordance with our tests and experiences in accordance with international standards at $23\pm 2^{\circ}\text{C}$ temperature and $50\pm 5\%$ relative humidity conditions. These values may vary depending on ambient conditions. High temperatures shorten the times, low temperatures lengthen them. Before starting the application, the user should test whether the product is suitable for the application and purpose. FIXA Yapı Chemicals San. Trade Ltd. Sti. is not responsible. This Technical Data Sheet remains valid until the next revision is published. FIXA reserves the right to change the values specified in this Technical Data Sheet, provided that the new version is published. It is the user's responsibility to check that the document is up-to-date. Please contact our sales department for more information.